

RENOLIT FEP

Extreme pressure lithium grease

Description

RENOLIT FEP greases are multi-purpose extreme pressure Lithium based greases with EP additives. They also contain special inhibitors to increase ageing stability and anti-corrosion properties. RENOLIT FEP greases have a very high resistance to mechanical loads, minimise wear under heavy and shock load conditions and give excellent protection against water washout and rusting. RENOLIT FEP greases are available in NLGI consistencies numbers 000, 00, 0, 1, 2, & 3.

Application

RENOLIT FEP greases exhibits good water washout resistance, coupled with a high dropping point. It is therefore suitable for the lubrication of both plain and rolling element bearings operating under high temperature, high load conditions. Operating temperatures up to 120°C can be withstood, or higher if the grease is frequently replenished.

RENOLIT FEP greases offer the following benefits:

- High temperature capability.
- Withstand high loads and shock loading.
- Resistant to water washout.
- Suitable for most bearing operations.

RENOLIT FEP greases can be used for most industrial and automotive applications, where loaded bearings and joints exist.



Typical Characteristics

| Properties | Units | S Value Te | | | | | | |
|---------------------------------|--------------------|------------|----------|---------|-----------|----------|----------|-------------|
| NLGI Grade | | 000 | 00 | 0 | 1 | 2 | 3 | DIN 51 818 |
| DIN Classification | ŀ | KP000K-20 | KPooK-20 | KPoK-20 | KP1K-20 | KP2K-20 | KP3K-20 | DIN 51 825 |
| Colour | Dark Brown | | | | | | | |
| Soap Type | Lithium | | | | | | | |
| Worked Penetration | 0.1 mm | 445-475 | 400-430 | 355-385 | 310-340 | 265-295 | 220-250 | ASTM D-217 |
| Dropping Point | °C | 150 min. | 165 min. | 170 min | .180 min. | 185 min. | 190 min. | ASTM D-566 |
| Base Oil Viscosity @ 40°C | mm ² /s | 190-220 | 190-220 | 190-220 | 190-220 | 190-220 | 190-220 | ASTM D-445 |
| Timken OK load | lbs. | 44-50 | 44-50 | 44-50 | 45-50 | 45-55 | 45-55 | ASTM D-2509 |
| Four ball EP-test, weld load | kg (F) | - | - | - | 260-280 | 260-280 | 260-280 | ASTM D-2596 |