



TURMOSYNTHGREASE ALN 1001

K P HC 1 N -40



Date of issue: 03.06.2014

TURMOSYNTHGREASE ALN 1001 is a synthetic special grease for high temperatures. It is based on synthetic hydrocarbons with a special thickener of high metal affinity.

TURMOSYNTHGREASE ALN 1001 is NSF/H1 approved as lubricant for which an incidental contact with food technically cannot be avoided.

NSF/H1-registration No.: 137417

Special properties

- High resistance towards oxidation and high temperatures
- High load carrying capacity
- Excellent corrosion and wear protection
- Long grease service life and wide operating temperature
- High lubricating effect at low friction coefficients



Product Characteristics	Value	Dimension	Norm / Standard
Colour	beige - reddish beige		
Density at 20°C	0,85	g/cm ³	DIN 51757
Operating temperature range	-40 to 140	°C	
Thickener	Aluminium special soap		
Base oil	Synthetic hydrocarbons		
Kin. viscosity of the base oil at 40°C	100	mm ² /s	DIN EN ISO 3104
Kin. viscosity of the base oil at 100°C	15,5	mm ² /s	DIN EN ISO 3104
Worked penetration	310 – 340	mm/10	DIN ISO 2137
Consistency class (NLGI)	1		DIN 51818
Dropping point	> 200	°C	DIN ISO 2176
Resistance to water	0 – 90		DIN 51807
Corrosion protection (SKF-Emcor)	0 / 0		DIN 51802

Application

TURMOSYNTHGREASE ALN 1001 is especially suitable for the lubrication of roller and plain bearings, linear sliding guides and recirculating ball screws.

TURMOSYNTHGREASE ALN 1001 shows an optimum behaviour at oscillation and environmental influences like hot and cold water.

Packaging units

25 x 100 g tubes, 20 x 400 g cartridges, 6 x 1 kg cans, 5 kg bucket, 10 kg hobbock, 25 kg hobbock, 50 kg hobbock, 180 kg drum

The products are subject to continuous strict production controls and comply with our own factory specifications. A warranty for each case cannot be given, due to the variety of relevant factors. Therefore, we recommend the implementation of field tests. Herewith, any liability is expressly excluded.

LUBRICANT CONSULT GMBH · Gutenbergstrasse 13 · 63477 Maintal (Germany)

Tel: +49 (0) 6109 / 7650-0 · Fax: +49 (0) 6109 / 7650-51 · E-Mail: webmaster@lubcon.com · Internet: <http://www.lubcon.com>