## **Technical Information**

## **LUBRICANT CONSULT GMBH**

Issued: 15.10.2009

Gutenbergstraße 13 · D-63477 Maintal - Germany · Telefon: +49-61 09 - 76 50-0 · Fax: +49-61 09 - 76 50-51 · Internet: www.lubcon.com

# **TURMOGREASE HDC 2**

**KP2N-30** 

#### **LUBCON- Special Grease**

**TURMOGREASE HDC 2** is a calcium sulfonate complex soap grease based on mineral oil with an extraordinary resistance to water and media. Under constant water influence this grease is neither washed out nor softening. **TURMOGREASE HDC 2** shows it's excellent lubricating and corrosion protection capacities even under very high pressure due to the combination of thickeners and additives.

#### **Quality Features**

- optimum water resistance and work stability
- high load carrying capacity, best behaviour to high temperatures
- improved performance to friction and wear
- very good corrosion protection, high metal affinity

Technical Data		TURMOGREASE HDC 2
Colour / Structure		brown / smooth, homogeneous
Temperature range short time		-30 °C up to +150 °C up to +200 °C
Thickener		Calcium sulfonate complex soap
Base oil		mineral oil
Base oil viscosity DIN EN	ISO 3104 at +40 ℃ at +100 ℃	410 mm²/s 26 mm²/s
Rest penetration DIN ISO 2137		288 <sup>1</sup> / <sub>10 mm</sub>
Worked penetration after 60 double strokes Worked penetration after 100 000 double strokes		290 <sup>1</sup> / <sub>10 mm</sub> 302 <sup>1</sup> / <sub>10 mm</sub>
Shell roller test ASTM D 1831 100 °C / 72 h		281 <sup>1</sup> / <sub>10 mm</sub>
Drop point DIN ISO 2176		>300 ℃
Corrosion protection ( Emcor ) DIN 51802		0 - 0
Water resistance DIN 51807 T2		1 - 80
Speed factor ( $n \times d_m$ )		300 000
Oil separation DIN 51817 at 40 at 10	0.00 0.00 0.00	0,8 % 6,0 %
FE 8-test DIN 51819 2-31312.A.36048-3000/10-120		500 h achieved
FE 9-test DIN 51821 A/1,5/3000-150 °C F <sub>10</sub>		142.74 h
FE 9-test DIN 51821 A/1,5/3000-150 °C F <sub>50</sub>		166.13 h

### **Application Area**

**TURMOGREASE HDC 2** is specially suitable for rolling and sliding bearings under vibrations, shock and compressive stress, specially at increased bearing temperature and load, in conveyor chains, dryers, stone quarries, in high capacity excavators, in shredder machines, in raw material processing machines and fans. **TURMOGREASE HDC 2** is used as a roler and sliding grease for low and medium bearing speeds in the steel and mining industry.

#### **Original Packaging**

6 x 1 kg cans, 20 x 400 g cartridges, 25 kg hobbocks, 180 kg drum (not returnable)