

G.A. PLEX-2 GREEN/100

HIGH PERFORMANCE GREASE FOR HIGH TEMPERATURES

DESCRIPTION

The **G.A. PLEX-2 GREEN/100** grease is a lithium-complex grease with EP additives for medium speed operated bearings and plain bearings. There is provided with resistance to water and excellent resistance to high temperatures and loads.

APPLICATIONS

The **G.A. PLEX-2 GREEN/100** grease can be used as long life grease in roller bearings, water pumps, electric motors, couplings, cardan joints, and in general wherever high efficiency greases are needed with severe requirements.

PROPERTIES

- High drop point.
- Good resistance to heavy loads.
- Outstanding anti-wear capacity.
- Insoluble in water.
- Good resistance to mechanical work.
- Good protection against corrosion.
- Good antioxidant capacity.
- Long life.

CAUTIONS

- The usual ones when handling and using lubricants.
- Avoid excess of grease as well as too frequent relubrication cycles.
- Keep the can closed to avoid contamination.
- Do not mix with different nature greases.

PHYSICAL-CHEMICAL CHARACTERISTICS

Colour	Green
Thickener	Lithium complex
Base oil nature	Mineral
Base oil viscosity at 40°C, (cSt)	110
NLGI consistency class	Grade 2
Penetration at 25°C 60 W, (0,1mm)	265 – 295
Penetration at 25°C 10 ⁵ W, (0,1mm)	Max. +50
Drop point, (°C)	Min. 260
EMCOR corrosion test	Max. 1
Copper corrosion, 24h / 100°C	Max. 1 b
4 balls machine: - Welding load, (kg) - Wear scare diameter 1h/40kg ,(mm) Oxidation stability 100h/100°C, (kg/cm²)	Min. 450 Max. 0,55 Max. 0,3
Evaporation loss, (%) - 22h/100°C - 22h/150°C Water resistance 90°C	Max. 0,5 Max. 2,5 Grade 1
Service temperature, (°C)	-30 to 160

14/12/2009 Page 1 of 1



The information contained in this document faithfully reflects our present technical knowledge, besides it provides a suitable description of the product characteristics and enumerates the different applications the product can be suitable for. In any case, the user will have to make sure of the adjustment of the product for each particular use. Brugarolas S.A. reserves the right to make modifications in the products after the date of edition of the present document in order to improve its quality and optimize its output. The values of the given physic-chemical characteristics are typical values. The specification sheets in force are at your disposal for each of the products.